RECEIVED CENTRAL FAX CENTER

DOCKET:

CU-2720

JUL 0 7 2004

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICANT:

Hisashi KUGIMOTO

SERIAL NO:

10/003,362

Group Art Unit: 1774

FILED:

November 15, 2001

) Examiner: Tamra Dicus

TITLE:

PROTECTION FILM FOR BASE SHEET

THE COMMISSIONER FOR PATENTS P.O. Box 1450 Alexandria, VA 22313-1450

AMENDED CLAIMS

(currently amended) A protection film for a base sheet of a lens sheet having 1. a lens surface formed of a UV-curable resin layer, the protection film comprising:

a resin film; and

an adhesive formed on one side of said resin film, said adhesive being separable together with allowing said protection film to be releasably seperable from said base sheet;

wherein a transmittance of ultraviolet rays, at least 82% of ultraviolet rays having a wavelength of 320 nm, through are transmitted through the protect on film is 82%-or more.

- (original) A protection film for a base sheet according to claim 1, wherein an 2. adhesive strength is from 0.4 to 2.3 N / 25 mm.
- 3. (cancelled)
- (previously presented) A protection film for a base sheet according to claim 1 wherein the adhesive contains a polyolefin-based resin component.
- (original) A protection film for a base sheet according to claim 1, wherein the material of the base sheet is an acrylic resin.

(currently amended) A lens sheet comprising:
a base sheet; and
a protection film comprising:

a resin film; and

an adhesive formed on one side of said resin film, said adhesive being separable together with allowing said protection film at to be release bly separable from said base sheet;

wherein a-transmittance-of ultraviolet rays, at least 82% of ultraviolet rays having a wavelength of 320 nm, through are transmitted through protection film is 82% or more.

7. (currently amended) A lens sheet according to claim 6, wherein the protection film is pasted from the side of the adhesive, a surface of the base sheet has coated thereon an antistatic agent containing a cationic surface active agent, and the base sheet has a surface resistivity after one year from production of $10^{12} \Omega / \Box$ or less.